

FA-S10 CONCRETE

High performance, multi-purpose, pre-packaged, concrete repair material. FA-S10 Concrete is a pre-blended, synthetic fiber reinforced, pre-packaged, high performance, cementitious, concrete repair material containing Portland cement, fly ash, air-entraining admixture, 10 mm (3/8 inch) stone and other carefully selected components.

FEATURES & BENEFITS

- Air-entrainment provides superior resistance to freeze-thaw cycling and salt-scaling in the presence of de-icing salts.
- Designed with natural normal-density non-reactive fine and coarse aggregates to eliminate potential alkali-aggregate reactivity (AAR).
- Properties similar to conventional concrete, thus offering excellent compatibility to parent concrete.
- Improved workability and finishability.
- Excellent pumpability.
- Reduced bleeding.
- Improved resistance to sulphate attack.
- Low permeability.
- Low shrinkage.
- All KING products are manufactured using ISO 9001:2008 Certified Processes.

USES

- Partial and full depth rehabilitation of concrete beams, columns, and/or soffits in bridges, parking garages, balconies or other concrete structures.
- Place FA-S10 Concrete at a minimum thickness of 38 mm (1½ inches).

PROCEDURES

Surface Preparation:

All surfaces to be in contact with FA-S10 Concrete must be free from dust, oil, grease or any other foreign substances that may interfere with the bond of the material. Remove all delaminated or unsound concrete providing a roughened surface and a minimum of 25 mm (1 inch) clearance behind any corroded reinforcing steel. The perimeter of the repair area should be sawcut a minimum of 20 mm (¾ inch). Clean the area to be repaired with potable water, leaving the concrete saturated but free of standing water (SSD).

Mixing:

Place 75% of required water into mixer and slowly introduce entire bag of FA-S10 Concrete. Add balance of required water slowly while mixer is running, not exceeding maximum recommended volume of water. **Maximum recommended volume of water is 3.0 litres (0.8 US gallon) per 30 kg (66 lb.) bag.** Continue mixing for a minimum of 3 minutes and stop only when material has obtained a consistent homogeneous mix.

Placing:

Mix and substrate temperatures should be maintained between 5 and 30°C (40 and 86°F). In cold weather, hot water may be used to increase mix temperature and avoid lengthy set times. Do not place FA-S10 Concrete when ambient temperature is below 5°C (40°F). Refer to ACI 306, "Cold Weather Concreting".

In warm weather, ice water may be used as mix water to cool mix temperature and avoid short working times. When ambient temperature is above 30°C (86°F). Refer to ACI 305, "Hot Weather Concreting".

Place material uniformly and consolidate by forcing it down to the surface of the parent concrete and around the underside of the rebar using a trowel, a wood float or by rodding the material. Ensure material has completely encapsulated any exposed rebar. For slab finishing, the use of a wood float is recommended.

Curing:

Curing is essential to optimize physical properties of the concrete and minimize plastic shrinkage. FA-S10 Concrete should be cured immediately after material has reached initial set in accordance with ACI 308 "Guide to Curing Concrete". Continuously moist cure for a minimum period of 7 days. Alternatively, moist cure for a minimum period of 24 hours and apply a curing compound that complies with ASTM C 309. Curing is particularly critical in rapid moisture loss conditions such as high temperatures, high winds and low humidity.

TECHNICAL DATA

The following data is representative of typical values achievable under laboratory conditions. Results in the field may vary.

MASS DENSITY		
ASTM C 39		2369 kg/m ³ (148 lb./ft ³)
COMPRESSIVE STRENGTH*		
ASTM C 39		
1 Day		15 MPa (2175 psi)
3 Day		30 MPa (4350 psi)
7 Day		35 MPa (5075 psi)
28 Day		45 MPa (6525 psi)
FLEXURAL STRENGTH		
ASTM C 78		
7 Day		5.1 MPa (740 psi)
28 Day		6.0 MPa (870 psi)
AIR CONTENT		
ASTM C 457		4.0 to 9.0%
MODULUS OF ELASTICITY		
ASTM C 469		
28 Day		28.4 GPa
POISSON'S RATIO		
ASTM C 469		
28 Day		0.23
BOND STRENGTH		
CSA A23.2-6B (MODIFIED)		1.75 MPa (250 psi)*

FA-S10 CONCRETE

BOND STRENGTH BY SLANT SHEAR

ASTM C 882

1 Day	7.5 MPa (1085 psi)
7 Day	18.1 MPa (2625 psi)

UNIAXIAL DRYING SHRINKAGE

ASTM C 157

3 Day	120 µm/m
28 Day	440 µm/m
60 Day	560 µm/m

BOILED ABSORPTION

ASTM C 642

6.8%

MAXIMUM VOLUME OF PERMEABLE VOIDS

ASTM C 642

14.8%

FREEZE-THAW RESISTANCE

ASTM C 666

97.1%
(Excellent durability factor)

SALT-SCALING RESISTANCE

ASTM C 672

50 cycles 0.31 kg/m² (0.06 lb./ft²)

RAPID CHLORIDE PERMEABILITY

ASTM C 1202

2000 Coulombs

* Bond strength achieved from independent jobsite testing.
Failure occurred in parent concrete.

Warranty: This product is designed to meet the performance specifications outlined in this product data sheet. If the product is used in conditions for which it was not intended, or applied in a manner contrary to the written recommendations contained in the product data sheet, the product may not reach such performance specifications. The foregoing is in lieu of any other warranties, representations or conditions, expressed or implied, including, but not limited to, implied warranties or conditions of merchantable quality or fitness for particular purposes, and those arising by statute or otherwise in law or from a course of dealing or usage of trade. [REV.0002_10/06/2014]

YIELD

30 kg (66 lb.) bag contains approximately 0.014 m³ (0.5 ft³).

PACKAGING

FA-S10 Concrete is normally packaged in 30 kg (66 lb.) triple lined bags and polywrapped on wooden pallets. All KING products can be custom packaged to suit specific job requirements.

STORAGE AND SHELF LIFE

Material should be stored in a dry covered area protected from the elements. Unopened bags have a shelf life of 12 months.

SAFETY PROCEDURES

FA-S10 Concrete contains Portland Cement. Normal safety-wear such as rubber gloves, dust mask and safety glasses used to handle conventional cement based products should be worn. Material Safety Data Sheets are available upon request.

KING PACKAGED MATERIALS COMPANY

Burlington Office
3385 Harvester Rd.
Burlington, ON
L7N 3N2
Phone: (905) 639-2993
Fax: (905) 333-3730

Boisbriand Office
3825 rue Alfred-Laliberté
Boisbriand, QC
J7H 1P7
Phone: (450) 430-4104
Fax: (450) 430-6855

Brantford Office
541 Oak Park Rd.
Brantford, ON
N3T 5L8
Phone: (519) 756-6177
Fax: (519) 756-7490

Sudbury Office
644 Simmons Rd.
Dowling, ON
P0M 1R0
Phone: (705) 855-1155
Fax: (705) 855-1122